

## 聚对苯二甲酸丁二醇酯(台湾长春) PBT Resin(CCP)

品级	IV (dl/g)	MI(235°C) (g/10min)	MI(250°C) (g/10min)	COOH (meq/kg)	ColoreL*	Colore b*	用途
1200-211E	0.68±0.015	112~140	160~210	≤25	≥85	≤2	电子 电器、 汽车 零件、 机械、 家用等
1200-211D	0.75±0.015	70~90	101~126	≤25	≥85	≤2	
1200-211D	0.75±0.015	70~90	101~126	7~17	85~89	0~2	
1200D	0.736~0.765	70~90	14~19.5	13~21	≥85	≤2	
1200-211DP	0.773±0.015	68~77	93~113	23~36	≥85	3.5	
1200-211L	0.79±0.015	58~72	82~105	≤25	≥85	≤2	
1200-211M	0.83±0.015	42~55	64~80	≤25	≥85	≤2	
1200-211M	0.83±0.015	42~55	64~80	7~15	85~89	0~2	
1200-211M	0.83±0.02	40~58	60~85	≤25	≥85	≤2	
1200-211F	0.85±0.015	40~50	55~72	≤25	≥85	≤2	
1100-211D	0.88±0.015	32~42	47~60	≤25	≥85	≤2	
1100-211A	0.922±0.015	26~33	38~47	≤25	≥85	≤2	
1100-211L	0.94±0.015	23~30	35~44	≤25	≥85	≤2	
1100-211LP	0.965±0.015	20~25	31~37	13~24	≥87	≤3.5	
1100-211MD	0.965±0.015	20~25	31~37	≤30	≥85	≤3	
1100-211M	1.00±0.015	18~22	27~32	≤30	≥85	≤2	
1100-211MB	1.06±0.015	14~18	20~26	≤30	≥85	≤2	
1100-211H	1.10±0.02	11~14	17~22	≤30	≥85	≤3	
1100-211H	1.10±0.02	11~14	17~22	11~25	85~89	0.4~2.4	
1100-211S	1.20±0.02	7~10	11~16	≤35	≥85	≤3	
1100-212S	-	8~11	13~17	≤25	≥85	≤4	
1100X	1.23~1.30	4~9	6~17	33~40	≥85	≤4	
1100-211XG	1.23~1.30	4~9	6~17	33~40	≥85	≤4	

1100-211X	1.30±0.02	4~7	6~12	≤40	≥85	≤4	
1100-211X	1.30±0.02	4~7	6~12	15~35	85~89	1~4	
1100-211XT	1.30±0.02	4~7	6~12	≤40	≥85	≤4	
1100-211XP	1.27±0.02	5~8	9~13	20~40	≥85	≤4	
1100-211XD	1.28±0.02	4~7	6~12	≤35	≥85	≤6.5	